



71 Western Avenue, Lynn, MA 01904 U.S.A

FAX (781) 598-4937 . (800) 323-0047

February 22, 2013

To: TruStone Distributors, Ltd.
Attn: Randy
PO Box 62297
Sharonville, OH 45262

Subject: Static Coefficient Of Friction Testing

Introduction -

Trusty-Step International received three pieces of tile (Timpled TruStone Travertine) from TruStone Distributors, Ltd. for testing. The static coefficient of friction values were determined as specified in ASTM-1028-06. Testing was conducted using dry and wet neolite.

Results -

<u>Material Identification</u>	<u>Static Coefficient of Friction Values (SCOF)</u>						<u>Average</u>	
	<u>Dry</u>			<u>Wet</u>			<u>Dry</u>	<u>Wet</u>
A, B, and C	.91,	.85,	.88	.51,	.59,	.61	.9	.7
	.84,	.86,	.88	.62,	.67,	.67		
	.94,	.90,	.88	.65,	.71,	.69		
	.85,	.89,	.88	.73,	.74,	.67		

Discussion -

To be considered slip resistant according to ASTM-1028-06, a minimum SCOF of 0.6 when tested dry or wet is required. The subject material does meet this requirement.